



材料鑒定工程實驗室-台北

試驗報告



報告編號: HB-23-10051

C-23-43133

頁數: 1 OF 3

報告發行日期: 113 年 01 月 12 日

工程名稱: 臺灣桃園國際機場第三航站區 景觀石材工程
業主: 桃園國際機場公司
監造單位: 台灣世曦工程顧問股份有限公司
承造商: 翔聯企業股份有限公司
委託單位: 翔聯企業股份有限公司
地址: 新北市五股區五權七路 10 號 8F
材料廠商: 翔聯企業股份有限公司
樣品名稱: 深灰色系花崗石
結構部位: 主體航廈景觀鋪面工程、主體航廈景觀設施工程、主體航廈景觀排水工程
送驗人員: 翔聯企業股份有限公司(陳信宏)
取樣日期: NA
試驗日期: 112 年 12 月 26 日
試驗日期: 112 年 12 月 26 日
試驗日期: 113 年 01 月 05 日 ~ 113 年 01 月 11 日
註: 1. 以上資料(送驗人員、會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供
2. 除非另有說明, 此報告結果僅適用於收取之試驗件
未經本公司事先書面同意, 此報告不可部分複製
3. 收件方式為實驗室收件; 收件地點: 新北市五股區(新北產業園區)五權路 55 號

試驗結果:

試驗項目	試驗方法	試樣編號	烘乾恆重(g)	浸水後表面乾重(g)	浸水水中重(g)	試驗結果			
						吸水率(%)	最大	最小	平均
吸水率(%)	CNS 11321:2000	1	539.06	539.41	345.57	0.06	0.06	0.05	0.05
		2	532.63	532.88	341.34	0.05			
		3	541.86	542.13	347.23	0.05			
		#吸水率規範值(%)							

試驗項目	試驗方法	試樣編號	烘乾恆重(g)	浸水後表面乾重(g)	浸水水中重(g)	試驗結果			
						體比重	最大	最小	平均
體比重	CNS 11321:2000	1	539.06	539.41	345.57	2.78	2.78	2.78	2.78
		2	532.63	532.88	341.34	2.78			
		3	541.86	542.13	347.23	2.78			
		#體比重規範值							

本報告若有提供規範要求值時, 該規範值僅供參考, 合格之判定以委託單位實際要求為準。

陳思銘


報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/terms-and-conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction clauses included therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its inspection only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
1 (886-2) 2299-3278
1 (886-2) 2299-7857

No. 35, Wu Chuan Road, New Taipei Industrial Park, Wu Ki District, New Taipei City 240016, Taiwan (248016)
新北市五股區新北產業園區五權路35號
www.sgs.com.tw

Member of SGS Group



Materials Engineering Laboratory - Taipei

TEST REPORT

REPORT NO: HB-23-10051

C-23-43133

PAGE: 1 OF 3

REPORT ISSUE DATE: 2024.01.12

PROJECT NAME: Taiwan Taoyuan International Airport T3, Hardscape Stone Engineering
OWNER: Taoyuan International Airport Corp.
GENERAL CONTRACTOR: Taiwan CTCI Corp.
CONTRACTOR: Xiang Lian Enterprise Co., Ltd.
SUBCONTRACTOR: Xiang Lian Enterprise Co., Ltd.
SUBCONTRACTOR ADDRESS: 8F, No. 10, Lane 7, Wufeng District, New Taipei City
SUPPLIER: Xiang Lian Enterprise Co., Ltd.
MATERIAL DESCRIPTION: Dark Grey Granite
STRUCTURED LOCATION: Main Concourse Pavement, Main Concourse Landscape, Main Concourse Drainage
WITNESS: Xiang Lian Enterprise Co., Ltd. (CHEN Shin-Hung)
TESTER: N/A
SAMPLING DATE: 2023.12.26
RECEIPT DATE: 2023.12.26
TESTING PERIOD: 2023.01.05 ~ 2024.01.11
NOTE: 1. All data (Sampling, Witness, Test Method, Quantities, Receipt Date and Test Period, excluding this date) in the above report is provided by the customer.
2. Unless otherwise stated, this report only applies to the test sample received.
No part of this report may be reproduced without prior written consent from this company.
3. Sample submission is at the Laboratory. Submission address: No. 55, Lane 7, Wufeng District, New Taipei City.

TEST RESULTS:

TEST ITEM	TEST METHOD	TEST MEM.	SPECIMEN NO.	OVEN-DRY WEIGHT (g)	WET WEIGHT AFTER IMMERSION (g)	WEIGHT IN WATER (g)	TEST RESULTS			
Absorption (%)	CNS 11321 :2000		1	539.06	539.41	345.57	0.06	MAX	MIN	AVERAGE
			2	532.63	532.88	341.34	0.05			
			3	541.86	542.12	341.23	0.06			
		# Absorption Standard Value (%)					Below 0.40			

TEST ITEM	TEST METHOD	TEST NO.	SPECIMEN NO.	OVEN-DRY WEIGHT (g)	WET WEIGHT AFTER IMMERSION (g)	WEIGHT IN WATER (g)	TEST RESULTS		
							MAX	MIN	AVERAGE
Bulk Specific Gravity	CNS 11321 :2000	1	539.06	539.41	345.57	2.78	2.78	2.78	2.78
		2	532.63	532.88	341.34	2.78			
		3	541.86	542.12	347.23	2.78			
# Bulk Specific Gravity Standard Value							Above 2.56		

If this report provides standard values, they are for reference only. The qualified judgment is based on the actual requirements of the commissioning unit.

陳思銘

REPORT SIGNATORY

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/terms-and-conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction clauses included therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its inspection only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
合泰檢驗科技股份有限公司
1 (886-2) 2299-3278
1 (886-2) 2299-7857

No. 35, Wu Chuan Road, New Taipei Industrial Park, New Taipei City 240016, Taiwan
(886-2) 2299-3278
(886-2) 2299-7857

Member of SGS Group

"For your reference, the document on the left is the original test report, and the one on the right is an AI-translated version. Please note that the official English test report is currently being processed."

試驗報告



報告編號：HB-23-10051

C-23-43133

頁 數： 2 OF 3

報告發行日期：113 年 01 月 12 日

試驗結果：								
試驗項目	試驗方法	試樣編號	#養護方式	試樣尺寸			抗壓強度 (kgf/cm ²)	試驗結果
				長(cm)	寬(cm)	高(cm)		
抗壓強度	CNS 11319 :2000	1	乾燥狀態	5.752	5.422	5.916	1342	1666
		2		5.732	5.726	5.966	1415	
		3		5.752	5.764	5.932	1591	
		4		5.762	5.744	5.972	1914	
		5		5.712	5.792	5.974	2066	
#抗壓強度規格值(kgf/cm ²)				1336 以上				

註：#因顧客未提供石材裂理方向，故無法出具垂直與平行裂理方向之抗壓強度。

試驗項目	試驗方法	試樣編號	#養護方式	試樣尺寸			試驗結果		
				長(cm)	寬(cm)	厚(cm)	彎曲強度(kgf/cm ²)	平均彎曲強度(kgf/cm ²)	標準差
彎曲強度	CNS 13976 :1997	1	乾燥狀態	36.082	4.587	3.027	194	184	19
		2		36.064	4.581	3.022	191		
		3		36.068	4.544	3.031	151		
		4		36.088	4.563	3.035	188		
		5		36.018	4.561	3.024	196		
		6							
#壓曲強度規範值(kgf/cm ²)				84.35 以上					

註：#因客戶未提供石材裂理方向，故無法出具垂直與平行裂理方向之彎曲強度。

試驗項目	試驗方法	試樣編號	養護方式	試樣尺寸			試驗結果	
				長(cm)	寬(cm)	厚(cm)	破壞模數(kgf/cm ²)	平均破壞模數(kgf/cm ²)
破壞模數	CNS 11322:2000	1	乾燥狀態	20.056	10.036	5.762	166	177
		2		20.064	10.064	5.743	188	
		3		20.082	10.038	5.759	168	
		4		20.068	10.092	5.747	181	
		5		20.052	10.012	5.771	184	
平均破壞模數(kgf/cm ²)				105.47以上				

註：#因客戶未提供石材裂理方向，故無法出具垂直與平行裂理方向之破壞模數。

本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.gps.gov.hk/Terms-and-Conditions>, and to the electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.gps.gov.hk/ETerms-and-Conditions>. Attention is drawn to the limitation of liability and limitation of jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of GCS's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized reproduction or use of this document may constitute an offence under the Copyright Ordinance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司

35, Wu Chyuan Road, New Taipei Industrial Park, Wu Ku District, New Taipei City 248016, Taiwan / 248016 新北市五股區新北產業園區五權路35號
 ☎ (886-2) 2299-3279 ☎ (886-2) 2299-7857 www.sgs.com.tw

Member of SGS Green

Test Results

Report No. : C-23-43133
Report No. : HB-23-10051
Report No. : C-23-43133
Page No. : 2 OF 3
Report Issue Date: JAN 12, 2024

HB-23-10051 /

Report No. : C-23-43133

Report No. : HB-23-10051

Report No. : C-23-43133

Page No. : 2 OF 3

Report Issue Date: JAN 12, 2024

Test Results:

Test Item	Test Method	Specimen No.	Curing Method	Specimen Dimensions:			Test Results:	
				Length(cm)	Width(cm)	Height(cm)	Compressive Strength (kg/cm ²)	Average Compressive Strength (kg/cm ²)
Compressive Strength	CNS 11319 : 2000	1	Dry State	5.752	5.742	5.916	1342	1666
		2		5.732	5.726	5.916	1415	
		3		5.752	5.764	5.932	1515	
		4		5.752	5.744	5.912	1914	
		5		5.712	5.742	5.974	2066	
# Compressive Strength Specification Limit (kg/cm ²)				1336 or more				

Note: # Since the customer did not provide the stone texture direction, the compressive strength perpendicular and parallel to the texture direction cannot be provided.

To the flexure direction cannot be provided.									
Test Item	Test Method	Specimen No.	Curing Method	Specimen Dimensions:				Test Results:	
				Length (cm)	Width (cm)	Thickness (cm)	Flexural Strength (kgf/cm ²)	Average Flexural Strength (kgf/cm ²)	Standard Deviation
Flexural Strength	CNS 13976 : 1997	1	Dry State	36.082	4.587	3.027	194	184	19
		2		36.084	4.587	3.022	191		
		3		36.088	4.544	3.031	151		
		4		36.088	4.564	3.033	188		
		5		36.088	4.561	3.024	196		
# Flexural Strength Specification Limit (kgf/cm ²)				84.35 or more					

Note: # Since the customer did not provide the stone texture direction, the flexural strength perpendicular and parallel to the texture direction cannot be provided.

Test Item		Test Method	Specimen No.	Curing Method	Specimen Dimensions:			Test Results:
					Length(cm)	Width(cm)	Thickness (cm)	Modulus of Rupture (kgf/cm ²)
Modulus of Rupture	CNS 11322 : 2000	Dry State	1		20.056	10.036	5.762	168
			2		20.054	10.036	5.743	168
			3		20.082	10.038	5.738	168
			4		20.068	10.032	5.747	181
			5		20.052	10.012	5.771	184
# Modulus of Rupture (kgf/cm ²)								108.47 or more

Note: # Modulus of Rupture Specification Limit (kgf/cm²) - 105.47 or more.

Note: # Since the customer did not provide the stone texture direction, the modulus of rupture perpendicular and parallel to the texture direction cannot be provided.

This document is issued by the Company in respect to its General Conditions of Service and/or Terms and Conditions, or overlaid, or revised or as available at http://www.ags.com.tw/Terms_and_Conditions and for electronic form documents, subject to Terms and Conditions for Electronic Documents at http://www.ags.com.tw/Terms_and_Conditions. Attention is drawn to the limitation of liability and indemnization and jurisdictions clauses defined therein. Any funder of the document is asserted that information contained therein reflects the reliance is a thing at the time of said intervention and within the terms of Chen's instructions. If any, Any Company's sole responsibility is as in client and this document does not encourage waste to a transaction from exercising all their rights and obligations under the transaction concerns. This document does not represent or constitute an offer, or any other financial product of the Company. Any unlawful or illegal act or omission of the acceptor of appearance of this document is unlawful if this informant may be processed to the lesser newness of report. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. TWF0070270

SGS Taiwan Ltd.
台資檢驗科技股份有限公司

35, Wu Chyuan Road, New Taipei Industrial Park, Wu Ku District, New Taipei City 248016 / 248016 新北市五股區新北產業園區五權路35號
1 (886-7) 2289-2570 1 (886-7) 2289-1997 www.ags.com.tw

Member of SGS Group

"For your reference, the document on the left is the original test report, and the one on the right is an AI-translated version. Please note that the official English test report is currently being processed."



材料鑒定工程實驗室-台北



Civil Engineering
Laboratory
1134

試驗報告



報告編號：HB-23-10051

C-23-43133

頁數：3 OF 3

報告發行日期：113 年 01 月 12 日

試驗結果：

試驗項目	試驗方法	試樣編號	長度 (cm)	寬度 (cm)	厚度 (cm)	試驗前 重量(g)	試驗後 重量(g)	試驗結果	
								腳踏磨損 抗力	腳踏磨損抗力 平均值
腳踏磨損抗力	CNS 11320 :2000	1	5.052	5.068	2.016	144.73	143.94	38	38
		2	5.044	5.062	2.048	146.37	145.64	41	
		3	5.062	5.058	2.028	143.41	142.58	36	
#腳踏磨損抗力規範值								25 以上	

- 註：1. 本試驗之磨料(60 號氧化鋁磨料 Norton Treatment 138S)已經停產，本實驗室採用 2A#60 棕色氧化鋁磨料(千象研磨材料股份有限公司)。
2. 腳踏磨損抗力試驗進行時之溫度為 22.0°C，相對濕度 49%。
3. 規範值依 CNS 14448:2000 花崗石石材之規定。
4. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路 55 號。
5. 樣品描述：石材。



MATERIAL ENGINEERING
LABORATORY - TAIPEI

TEST REPORT

Report No. : HB-23-10051

C-23-43133

Page : 3 OF 3

Report Date : 113th Year 01 Month 12 Day

TEST RESULTS:

Test Item	Test Method	Specimen No.	Length (cm)	Width (cm)	Thickness (cm)	Weight Before Test (g)	Weight After Test (g)	Test Results	
								Abrasion Resistance	Abrasion Resistance
Sample No.	CNS 11330 :2000	1	5.052	5.068	2.016	144.73	143.94	38	38
		2	5.044	5.062	2.048	146.37	145.64	41	
		3	5.062	5.058	2.028	143.41	142.58	36	
Abrasion Resistance Results								25 or more	

- Notes: 1. The abrasive for this test (609 Alumina Oxide Norton Treatment 138S) is discontinued, this laboratory adopts 2A#60 Brown Pased Alumina abrasive (provided by Chien Cheng Abrasive Co., Ltd.).
2. The temperature and relative humidity during the abrasion resistance test were 22.0°C and 49%, respectively.
3. The specifications are in accordance with CNS 14448:2000 for "Granite and Other Building Stones".
4. The location where this test report was generated: No. 55, Wuquan Rd., Wuku Dist., New Taipei City.
5. Sample Description: Stone Material.

本報告若有提供規範要求值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Absence is shown to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, copying or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of this law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司

35, Wu Chuan Road, New Taipei Industrial Park, Wu Ku District, New Taipei City 240016, Taiwan
T (886-2) 2299-3279 F (886-2) 2299-7857

www.sgs.com.tw
Member of SGS Group

2WE 0070278

新北市五股區新北產業園區五權路55號

This report is provided for the purpose of specification requirements, the specifications are for reference only, the confirmation of compliance is subject to the actual requirements of the entrusting party.

SGS Taiwan Ltd.
Taiwan Testing Technology Co., Ltd.

35, Wu Chuan Road, New Taipei Industrial Park, Wu Ku District, New Taipei City 240016, Taiwan
T (886-2) 2299-3279 F (886-2) 2299-7857

www.sgs.com.tw
Member of SGS Group

2WE 0070278

35, Wu Chuan Road, New Taipei Industrial Park, New Taipei City

"For your reference, the document on the left is the original test report, and the one on the right is an AI-translated version. Please note that the official English test report is currently being processed."